

Modified Polymer Rubber Gel Preformed Membrane Sheet

GTR-750

RAPID PERFORMANCE

PRODUCT DATA: Below Grade/Above Grade Waterproofing 8-0301.85

Description

GTR-750 is a composite preformed waterproofing membrane which integrates a modified polymer rubber gel with a high-performance polyethylene protection sheet to create a hybrid, integrated waterproofing membrane. GTR-750 is used for above and below grade construction. Due to its self-sealing characteristics, GTR-750 is ideal for effective, permanent waterproofing. GTR-750 is self-seaming and applied without primer, reducing overall project time and cost. GTR-750 is applied by simply rolling onto the substrate and applying pressure to assure uniform adhesion.

Uses

GTR-750 is applied in both above grade and below grade applications. GTR-750 is suitable for new construction and some repair applications.

Applications include the following types of waterproofing: horizontal positive side waterproofing and vertical positive side waterproofing

Areas of application include: Plaza decks, Elevator Pits, Tunnel Lining, Poured wall foundations, Block wall foundations, Brick wall foundations, Granite/limestone foundations, Split slab construction, Green roofs, IRMA roofs

Preparation

Surfaces shall be structurally sound and free of voids, spalled areas, loose aggregate and sharp protrusions. Smooth surface irregularities of more than 80mils. Remove contaminants such as grease, oil and wax from exposed surfaces. Remove dust, dirt, loose stone and debris. No surface primer is necessary. Application should proceed only in dry weather and when substrate temperature is above 15° F

Features:

Self seaming membrane does not require heat welding of seams or accessory seaming tapes. Creates tight bond with itself.

Self sealing, Self healing, membrane.

Remains permanently flexible. Durable to vibration and continuous movement.

No extensive surface preparation or primers needed. Easy to apply, safe, easily stored and transported.

Durable sheet protection combined with dynamically responsive non-curing gel.

Chemically resistant, hydrocarbon resistant, resistant to freeze/thaw cycling, dry/wet cycling.

Benefits:

True monolithic sheet system. Eliminates potential leak sources. Quality control and productivity enhancement.

Easy detailing of penetrations, self heals under hydrostatic pressure

Waterproofing is maintained. No loss of adhesion or separation.

Cost-effective, reduce labor, save time, fewer application mistakes.

Responds to substrate movement, thermal expansion/contraction without separation or debonding

Effective in adverse environmental conditions.

Packaging

GTR-750 is packaged in 3.3ft x 32.8ft Rolls.

Yield

107.64 sq. ft. per roll

Transportation

GTR-750 is classified as a DOT non-hazardous material.

Shelf Life

Indefinite, when stored according to recommended storage guidelines.

Storage

Store unopened rolls in clean, dry conditions at 40° to 80° F.

Technical Data Composition

GTR-750 is a modified polymer rubber gel infused with special adhesives combined with a 40mil mod bit protection sheet to create a hybrid, integrated waterproofing membrane.

Property	Value
pH	7.5 ~8.0
Specific Gravity	1.1 ~ 1.3
Freezing Point	Below -25° F
Physical State	Sheet
Appearance	Black/Black
Thickness	75.5 mil

Test Item	Unit	Test Results	Test Method
Thickness, Average	Mils (mm)	75.5 (1.9)	
Tensile Performance Tensile Strength	N/mm	13.5 (Length) 10.4 (Width)	KS F 4917
Tensile Performance Extension Percentage	%	47.2 (Length) 40.0 (Width)	
Tearing Strength	N	118.1 (Length) 118.1 (Width)	
Temperature Performance Tensile Strength at -4° F	N/mm	18.4 (Length) 14.3 (Width)	KS F 4934
Tensile Performance Extension Percentage at - 4° F	%	56.6 (Length) 162.0 (Width)	
Temperature Performance Tensile Strength at 140° F	N/mm	3.0 (Length) 2.1 (Width)	
Tensile Performance Extension Percentage at 140° F	%	224.1 (Length) 225.9 (Width)	

How to Apply GTR-750:

Preparation

Surfaces shall be structurally sound and free of voids, spalled areas, loose aggregate and sharp protrusions. Smooth surface irregularities of more than 80mils. Remove contaminants such as grease, oil and wax from exposed surfaces. Remove dust, dirt, loose stone and debris. No surface primer is necessary. Application should proceed only in dry weather and when substrate temperature is above 15° F

Application

Remove release film and roll GTR-750 onto the surface. Apply pressure in a smooth continuous movement making sure that GTR-750 adheres evenly over the entire surface. Lap seams 4". Detail penetrations, corners and joints with GTR- detail patch.

Clean Up

Remove waste and debris from job site.

Limitations

Do not apply GTR-750 in areas where it will be permanently exposed to sunlight, weather or traffic. GTR-750 is not recommended as a pond or tank liner except when installed between concrete slabs. GTR- 750 is not a UV rated material, if should be protected from UV and potential damage immediately after installation or flood test. Backfilling or protection course installation should be done as soon as possible.

Health and Safety

Avoid excess contact with skin. Keep out of eyes and mouth. Wear suitable gloves and safety glasses. See MSDS.

For Technical Assistance Contact:



RE-Systems Group Americas, Inc.
1136 114th Ln NW Suite 400
Minneapolis, MN 55448
P: 612.872.1900
F: 612.872.1902
www.re-systemsgroup.com

GTS and GEL-TECH SYSTEMS are registered trademark and patent covered products. All information and statements including test results and recommendations are believed to be truthful and accurate, however The RE-Systems Group Americas, Inc. does not warrant or guarantee anything contained in this document. Product users should verify suitability independently. RE-Systems Group Americas, Inc. MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS.